PIMA Technical Bulletin #117

Polyiso Insulation Types


A Guide to the Classification of Polyiso Board Insulation Products

About Polyiso Insulation

Polyiso is a rigid foam insulation used in more than 70% of commercial roof construction and offers a continuous insulation solution for commercial and residential wall assemblies. As one of North America's most widely used and readily available building products, Polyiso is a cost-effective insulation option for reducing building energy use and improving the overall service-life of roofs and walls.

The benefits of using Polyiso include:

- High R-value per inch of thickness
- Excellent fire test performance
- Extensive building code approvals
- Cost-effective continuous insulation (ci) solution
- Compatible with most roof and wall systems
- Dimensional stability
- Compressive strength
- Moisture resistance
- Thinner walls and roofs with shorter fasteners
- Long service life
- Preferred insurance ratings
- Virtually no global warming potential
- Zero ozone depletion potential
- Recyclable through reuse
- Recycled content (amount varies by product)
- Regional materials (nationwide production network)



Facers and facing materials serve a variety of functions in the production and use of polyiso insulation. Beginning with the manufacture of polyiso board, they are used to contain the foam core during the production process. After manufacture, they add strength and dimensional stability to the finished insulation board. Facers and facing materials also may serve a number of functions during the working life of the product beyond contributing to strength and dimensional stability. Depending on the type of facer or facing material, these functions may include providing a substrate compatible with other building materials, reducing water absorption and water vapor permeance, restricting air movement, increasing thermal resistance, creating a drainage plane to shed water and adding radiative properties to wall and roof assemblies.

Selecting Polyiso Insulation Types

The specifier or buyer of polyiso insulation may base the selection of a particular product type in part on the attributes of the facer or facing material incorporated into the product. As an example, ASTM C1289 Type I polyiso uses an aluminum foil facer that provides a maximum vapor permeance of 0.3 perms, which is generally considered to be impermeable to water vapor. For the specifier or buyer seeking to install a vapor retarder within a roof or wall assembly, this product may provide the desired vapor retarder, as long as the product is installed in accordance with the manufacturer's instructions to achieve vapor retardancy. In a similar manner, the buyer or specifier seeking a suitable substrate for nailing of shingles or other roof coverings directly over the product may select ASTM C1289 Type V polyiso that uses a facing material of oriented strand board (OSB) or plywood as an upper layer, as long as the product is installed in accordance with the manufacturer's instructions for suitability as a nailable substrate.

In all cases, the proper selection of any type of polyiso insulation shall include the installation of the product in accordance with the written specifications and instructions of the manufacturer. In addition, in situations



where the polyiso insulation is incorporated into a proprietary roof or wall system assembly, the written specifications and instructions of the roof or wall system manufacturer or supplier also shall be followed. Finally, because roof and wall systems are subject to a variety of building codes, the requirements of the building code as adopted by the relevant governing authority also shall be followed.

Types of Facers and Facing Materials

The following generic types of facers typically are used in the manufacturer of polyiso board insulation for building construction applications.

- Foil Facer (FF). FF is composed of aluminum foil that may be coated and/or laminated to a supporting substrate. (See Note 1.)
- Glass Reinforced Facer (GRF). GRF is composed of a cellulosic fiber felt containing glass fibers. (See Notes 1 and 2.)
- Coated Glass Facer (CGF). CGF is composed of coated polymer bonded fibrous glass mats bonded with organic polymer binders and coated with organic polymer, clay, or other inorganic substances. The coating may be applied either to the glass fibers before bonding into mats or after the glass mats are bonded together. (See Notes 1 and 3.)
- All Glass Facer (AGF). AGF is composed of uncoated fibrous glass mats bonded with organic polymer binders without an additional coating. (See Notes 1 and 3.)
- Perlite Board. Perlite board used as a facer shall conform to ASTM Standard Specification
- Cellulosic Fiber Board. Cellulosic fiber board used as a facer shall conform to ASTM Standard Specification C208.
- Oriented Strand Board (OSB). OSB used as a facer shall conform to U.S. Voluntary Product Standard PS 2-10.
- Plywood. Plywood used as a facer shall conform to U.S. Voluntary Product Standard PS 1-09 or PS 2-10.
- Glass Mat-Faced Gypsum Board. Glass mat-faced gypsum board used as a facer shall conform to ASTM Standard Specification C1177/C1177M

- 1. Because no current ASTM standards are available for FF, GRF, CGF, and AGF products, the definitions provided above rely on generic descriptions of facer and laminate materials currently available in the marketplace using terms common to these products. These facers are produced by a number of different manufacturers in North America, and the properties of the facers themselves may be altered when used to manufacture polyiso boards. In addition, the properties of polyiso boards, such as water absorption, vapor permeance, strength, and dimensional stability may vary depending on the exact composition of a given type of facer. However, in all cases the final product shall always meet the requirements of C1289.
- 2. Felts are made with organic fibers, inorganic fibers, or mixtures of organic and inorganic fibers.
- 3. Glass fiber mats are used uncoated or coated.

Polyiso Insulation Product Classification Table

This table provides information regarding the type of facers and/or laminates and typical application for each ASTM C1289 classification of polyiso board insulation.

| ASTM C1289 Classification | | Facer or Facing Material | Facer or Facing Material | Compressive | |
|------------------------------|-------|--|-----------------------------|---|-------|
| Туре | Class | Side 1 | Side 2 | Strength | Notes |
| I | 1 | FF both sides | | 16 psi | |
| I | 2 | FF both sides | | 16 psi | |
| Ш | 1 | GRF both sides | | Grade 1: 16 psi | |
| Ш | 2 | CGF both sides | | Grade 2: 20 psi | |
| Ш | 3 | AGF both sides | | Grade 3: 25 psi | |
| | | | | (Note: All grades apply to Type II Class 1, 2, or 3.) | |
| II | 4 | CGF or AGF both sides | | Grade 1: 80 psi Grade 2: 110 psi Grade 3: 140 psi | 2 |
| III | n/a | Perlite Board | GRF, CGF, or AGF | 16 psi | 1 |
| IV | n/a | Wood Fiber Board | GRF, CGF, or AGF | 16 psi | 1 |
| V | n/a | Oriented Strand Board (OSB) or Plywood | GRF, CGF, or AGF | 16 psi | 1 |
| VII | n/a | Glass Mat-Faced Gypsum Board | GRF, CGF, or AGF | 16 psi | 1 |

^{1.} Orientation of the facer side shall be in accordance with manufacturer instructions for the specific application

ABOUT PIMA

Since 1987, PIMA has served as the voice of the North American rigid polyiso insulation industry. PIMA is a leading advocate for safe, cost-effective, sustainable, and energy-efficient construction. The Association is comprised of polyiso manufacturers and industry suppliers, and represents the public policy interests of its membership at the local, national, and international levels to advance high-performance building practices.

PIMA produces technical bulletins to address key topics related to polyiso insulation. These publications inform architects, specifiers, and contractors about the performance characteristics of polyiso insulation. Always consult individual manufacturers for product specific information, including product data sheets and installation instructions.

For more information on polyisocyanurate insulation, visit www.polyiso.org



















^{2.} Available in maximum 1/2" thickness.